

WHEN YOU NEED TO BE SURE

## DRI SPONGE IRON



[www.sopelinc.com](http://www.sopelinc.com)



[info@jsopelinc.com](mailto:info@jsopelinc.com)



+82-10-3422-2885



202HO 101 DONG HANSHIN VILLAT 258-29 HOWON DONG UIJEONG BU SHI GYEOUNGI DO SOUTH KOREA.

**SOPEL INC**

**DRI SPONGE IRON**

No	ELEMENT	RESULT
1	FE TOTAL (%)	MIN88<TOTAL< 92 MAX
2	FE METAL (%)	82< METAL< 84
3	MD (%)	MIN 91< MD< 93 MAX
4	C (%)	1.5 MIN
5	SIO2 (%)	4 MAX
6	AL2O3 (%)	0.5 MAX
7	S (%)	0.008 MAX
8	P (%)	0.05 MAX
9	SIZING	9-18 MM, 90%
10		6.3-9 MM, 5%



**D.R.I SPONGE IRON**

+82-10-3422-2885



info@sopelinc.com



Jee Woon Kim Mr.



202HO 101 DONG HANSHIN VILLAT 258-29 HOWON DONG UIJEONG BU SHI GYEONGGI DO SOUTH KOREA.